

AMENDMENTS TO THE CLAIMS:

This listing of claims will replace all prior versions, and listings, of claims in the application:

LISTING OF CLAIMS:

1. - 21. (Canceled)

22. (Currently Amended) A composition ~~based on~~ comprising zirconium oxide and cerium oxide, the composition comprising having a zirconium oxide proportion of at least 50% by weight, a maximum reducibility temperature of at most 500°C, and a specific surface area of at least 40m²/g after calcination for 6 hours at 500°C, and comprising a predominant ~~being in the form of a~~ tetragonal phase.

23. (Previously Presented) The composition as claimed in claim 22, further comprising at least one lanthanide other than cerium.

24. (Previously Presented) The composition as claimed in claim 23, wherein the lanthanide is lanthanum, neodymium or praseodymium.

25. (Currently Amended) The composition as claimed in claim 22, having comprising a zirconium oxide content of at least 65% by weight.

26. (Currently Amended) The composition as claimed in claim 22, ~~having~~ comprising a maximum reducibility temperature of at most 480°C, ~~optionally at most 400°C.~~

27. (Currently Amended) The composition as claimed in claim 22, ~~having~~ comprising a specific surface area of at least 70 m²/g, ~~optionally at least 80 m²/g, after calcination at 500°C for 6 hours.~~

28. (Currently Amended) The composition as claimed in claim 22, ~~having~~ comprising a specific surface area of at least 30 m²/g after calcination at 900°C for 6 hours.

29. (Currently Amended) The composition as claimed in claim 28, ~~having~~ comprising a specific surface area of at least 45 m²/g after calcination at 900°C for 6 hours.

30. (Currently Amended) The composition as claimed in claim 22, ~~having~~ comprising a specific surface area of at least 25 m²/g after calcination at 1000°C for 6 hours.

31. (Currently Amended) The composition as claimed in claim 22 23, wherein ~~it~~ the composition is in the form of a solid solution of cerium, ~~optionally with the lanthanide other than cerium,~~ in zirconium oxide.

32. (Withdrawn) A method of preparing a composition as claimed in claim 22, wherein it comprises the following steps:

(a) forming a mixture comprising a zirconium compound, a cerium compound and, optionally, a lanthanide other than cerium;

(b) mixing said mixture with a basic compound, to obtain a precipitate;

(c) heating said precipitate in an aqueous medium; and, then,

(d) either firstly adding an additive, selected from the group consisting of anionic surfactants, nonionic surfactants, polyethylene glycols, carboxylic acids, salts of carboxylic acids, and surfactants of the carboxymethylated fatty alcohol ethoxylate type in the medium resulting from the previous step (c), and, then, optionally separating said precipitate; (d') or, firstly separating the precipitate obtained in step (c) and, then, adding said additive to the precipitate; (e) subjecting to a milling operation the precipitate obtained in step (d) or (d'); and (f) calcining the precipitate obtained in step (e).

33. (Withdrawn) The method as claimed in claim 32, wherein in step (e) the precipitate is calcined either in an oxidizing atmosphere or firstly in an inert gas and then secondly in an oxidizing atmosphere.

34. (Withdrawn) The method as claimed in claim 32, wherein, the zirconium compound, the cerium compound and the lanthanide other than cerium, is a nitrate, acetate, chloride or ceric ammonium nitrate compound.

35. (Withdrawn) The method as claimed in claim 32, wherein the zirconium or cerium compound is a sol.

36. (Withdrawn) The method as claimed in claim 32, wherein, in the mixture of step (a), the cerium compound presents cerium in the Ce(III) form and during step (a) or during step (b), an oxidizing agent is added.

37. (Withdrawn) The method as claimed in claim 32, wherein in step b) a basic compound the mixture is further being added into a solution of this basic compound.

38. (Withdrawn) The method as claimed in claim 32, wherein in step (c) the precipitate is being heated to a temperature of at least 100°C.

39. (Withdrawn) The method as claimed in claim 32, wherein in step (e), the milling is a wet milling operation.

40. (Withdrawn) The method as claimed in claim 32, wherein in step (e), the milling is carried out by subjecting a suspension of the precipitate to a shearing action.

41. (Currently Amended) A catalytic system, comprising a the composition as claimed in claim 22.

42. (Withdrawn) A method of automobile postcombustion catalysis of exhaust gases of an internal combustion engine, said method comprising the step of treating said exhaust gases with a catalytic system as claimed in claim 41.

43. (New) The composition as claimed in claim 26, having a maximum reducibility temperature of at most 400°C.

44. (New) The composition as claimed in claim 27, having a specific surface area of at least 80m²/g after calcination at 500°C for 6 hours.

45. (New) The composition as claimed in claim 31, wherein the solid solution further comprises the at least one lanthanide other than cerium.